



СКИФ-М

Техническое приложение

Сравнительная таблица обрабатываемых материалов

ISO	Страна							k _c 1.1	m _c	Группа обработки
	Россия	Великобритания	США	Германия		Франция	Испания			
	Стандарт									
	ГОСТ P	BS	AISI/SAE	W.-Nr.	DIN	AFNOR	UNF			
P	Нелегированная сталь									
	15	080M15	1015	1.0401 / 1.1141	C15/ Ck15	11SMnPb28	F.111/ C15K	1350	0,21	1
	20	050A20	1020	1.0402	C22	CC20	F.112	1350	0,21	1
		230M07	1213	1.0715	9SMn28	S250	11SMn28	1350	0,21	1
			12L13	1.0718	9SMnPb28	S250Pb	11SMnPb28	1350	0,21	1
	A12			1.0722	10SPb20	10PbF2	10SPb20	1350	0,21	1
		240M07	1215	1.0736	9SMn36	S300	12SMn35	1350	0,21	1
			12L14	1.0737	9SMnPb36	S300Pb	12SMnP35	1350	0,21	1
	25		1025	1.1158	Ck25			1350	0,21	1
	35Г2	150M28	1330	1.1170	28Mn6	20M5		1500	0,22	2
	A30	212M36	1140	1.0726	35S20	35MF4	F210G	1525	0,22	2/3
	35	060A35	1035	1.0501	C35	CC35	F.113	1525	0,22	2/3
	45	080M46	1045	1.0503	C45	CC45	F.114	1525	0,22	2/3
	40Г	151M36	1039	1.1157	40Mn4	35M5		1525	0,22	2/3
	35ГЛ		1335	1.1167	36Mn5	40M5	36Mn5	1525	0,22	2/3
		060A35	1035	1.1183	Cf35	XC38TS		1525	0,22	2/3
	45	080M46	1045	1.1191	Ck45	XC42	C45K	1525	0,22	2/3
	50	060A52	1050	1.1213	Cf53	XC48TS		1525	0,22	2/3
	55	070M55	1055	1.0535 / 1.1203	C55 / Ck55	XC55	C55K	1675	0,24	3
	60	080A62	1060	1.0601	C60	CC55		1675	0,24	3
	60Г	080A62	1060	1.1221	Ck60	XC60		1675	0,24	3
	Низколегированная сталь									
	ШХ15	65A99	52100	1.3505	100Cr6	100C6	F.131	1675	0,24	6/7
	15НМ	1501-240	ASTM A204Gr.A	1.5415	15Mo3	15000	16Mo3	1675	0,24	6/7
		1503-245-420	4520	1.5423	16Mo5		16Mo5	1675	0,24	6/7
	15ГНЛ		ASTM A350LF5	1.5622	14Ni6	16N6	15Ni6	1675	0,24	6/7
	12ХН3А		3415	1.5732	14NiCr10	14NC11	15NiCr11	1675	0,24	6/7
	20ХН4ФА	655M13	3415, 3310	1.5752	14NiCr14	12NC15		1675	0,24	6/7
	18Х2Р4ВА	820A16		1.6587	17CrNiMo6	18NCD6	14NiCrMo13	1675	0,24	6/7
	18ХГ	527M20	5115	1.7131	16MnCr5	16MC5	16MnCr5	1675	0,24	6/7
	15ХМ			1.7262	15CrMo5	12CD4	12CrMo4	1675	0,24	6/7
	12ХМ	151-620Gr27	ASTM A182	1.7335	13CrMo4 4	15CD3.5	14CrMo45	1675	0,24	6/7
	12Х2МФА	1501-622	ASTM A182	1.7380	10CrMo910	12CD9,10	TU.H	1675	0,24	6/7
	12Х1МФ	1503-660-440		1.7715	14MoV6 3		13MoCrV6	1675	0,24	6/7
	20ХГНМ	805M20	8620	1.6523	21NiCrMo22	20NCD2	20NiCrMo2	1725	0,24	6/8
	15Х	523M15	5015	1.7015	15Cr3	12C3		1725	0,24	6/8
	35Х	530A32	5132	1.7033	34Cr4	32C4	35Cr4	1725	0,24	6/8
	20ХМ	1717CDS110	4130	1.7218	25CrMo4	25CD4	55Cr3	1725	0,24	6/8
	35ХН2МЛ	640A35	3135	1.5710	36NiCr6	35NC6		1800	0,24	6/9
	55C2	250A53	9255	1.0904	55Si7	55S7	56Si7	1775	0,24	6/9
	60C2		9262	1.0961	60SiCr7	60SC7	60SiCr8	1775	0,24	6/9
	40ХН2МА	816M40	9840	1.6511	36CrNiMo4	40NCD3	35NiCrMo4	1775	0,24	6/9
		311-Type 7	8740	1.6546	40NiCrMo22		40NiCrMo2	1775	0,24	6/9
	38ХН2МА	817M40	4340	1.6582	35CrNiMo6	35NCD6		1775	0,24	6/9
	40Х	530M40	5140	1.7035	41Cr4	42C4	42Cr4	1775	0,24	6/9
	50ХГА	527A60	5155	1.7176	55Cr3	55C3		1775	0,24	6/9
	35ХМ	708A37	4137, 4135	1.7220	34CrMo4	35CD4	34CrMo4	1775	0,24	6/9
	38ХМА	708M40	4140, 4142	1.7223	41CrMo4	42CD4TS	42CrMo4	1775	0,24	6/9
	40ХН2МА	708M40	4140	1.7225	42CrMo4	42CD4	42CrMo4	1775	0,24	6/9
	30Х3ВА	722M24		1.7361	32CrMo12	30CD12	F.124.A	1775	0,24	6/9
	50ХФА	735A50	6150	1.8159	50CrV4	50CV4	51CrV4	1775	0,24	6/9
	38ХМЮА	905M39		1.8509	41CrAlMo7	40CAD6,12	41CrAlMo7	1775	0,24	6/9
	40Х5МФ	897M39		1.8523	39CrMoV13 9			1775	0,24	6/9
	9ХГ	BL3	L3	1.2067	100Cr6	Y100C6	100Cr6	1775	0,24	6/9
	ХВГ			1.2419	105WCr6	105WC13	105WCr5	1775	0,24	6/9
	5ХНМ		L6	1.2713	55NiCrMoV6	55NCDV7	F.520.S	1775	0,24	6/9
	5ХВ2С	BS1	SI	1.2542	45WCrV7		45WCrSi8	1775	0,24	6/9
	Высоколегированная сталь									
	4Х5МФ1С	BH13	H13	1.2344	X40CrMoV51	Z40CDV5	X40CrMoV5	2450	0,23	10/11
		1501-509;510	ASTM A353	1.5662	X8Ni9		XBNI09	2450	0,23	10/11