


Техническое приложение



ISO	Страна							k _c 1.1	m _c	Группа обработки	
	Россия	Великобритания	США	Германия		Франция	Испания				
	Стандарт										
	ГОСТ Р	BS	AISI/SAE	W.-Nr.	DIN	AFNOR	UNF				
P	15ГН4М		2515	1.5680	12Ni19	Z18N5		2450	0,23	10/11	
	18Х2Н4МА	832М13		1.6657	14NiCrMo134		14NiCrMo131	1675	0,24	10/11	
	X12	BD3	D3	1.2080	X210Cr12	Z200C12	X210Cr12	2450	0,23	10/11	
	X6ВФ	BA2	A2	1.2363	X100CrMoV51	Z100CDV5	X100CrMoV5	2450	0,23	10/11	
	3Х2В8Ф	ВН21	H21	1.2581	X30WCrV9 3	Z30WCV9	X30WCrV9	2450	0,23	10/11	
	40Х9S2	401 S45	HW3	1.4818	X45GrSi93	Z45CS9	F322	2450	0,23	10/11	
	P6M5K5			1.3243	S 6-5-2-5	Z85WDKCV	HS6-5-2-5	2450	0,23	10/11	
	P18K5Ф2			1.3255	S 18-1-2-5	Z80WKCV	HS18-1-1-5	2450	0,23	10/11	
	P6M5			1.3343	S 6-5-2	Z85WDCV	HS6-5-2	2450	0,23	10/11	
				1.3348	S 2-9-2	Z100WCWV	HS2-9-2	2450	0,23	10/11	
	P18			1.3355	S 18-0-1		HS18-0-1	2450	0,23	10/11	
	X12МФ			1.2601	X165CrMoV 12		X160CrMoV12	2450	0,23	10/11	
	X12ВМ			1.2436	X210CrW12		X210CrW12	2450	0,23	10/11	
	110Г13Л	Z1201VU2		1.3401	G-X120Mn12	Z120M12	X120Mn12	3300	0,24	11	
	Нержавеющая ферритная и мартенситная сталь										
	08Х13	403S17	403	1.4000	X7Cr13	Z6C13	F.3110	1875	0,21	12/13	
				1.4001	X7Cr14		F.8401	1875	0,21	12/13	
	12Х13	410S21	410	1.4006	X10G13	Z10C14	F.3401	1875	0,21	12/13	
	12Х17	430S17	430	1.4016	X8Cr17	Z8C17	F.3113	1875	0,21	12/13	
	40Х13	420S45		1.4034	X46Cr13	Z40CM	F.3405	1875	0,21	12/13	
		405S17	405	1.4002	X6CrAl13	Z8CA12		1875	0,21	12/13	
	20Х13	420S37	420	1.4021		Z20C13		1875	0,21	12/13	
	20Х17Н12	431S29	431	1.4057	X22CrNi17	Z15CNI6.02	F.3427	1875	0,21	12/13	
	08Х18Т		430F	1.4104	X12CrMoS17	Z10CF17	F.3117	1875	0,21	12/13	
		434S17	434	1.4113	X6CrMo17	Z8CD17.01		1875	0,21	12/13	
		425C11		1.4313	X5CrNi13 4	Z4CND13.4M		1875	0,21	12/13	
	10Х13СЮ	403S17	405	1.4724	X10CrAl13	Z10C13	F.311	1875	0,21	12/13	
	15Х18СЮ	430S15	430	1.4742	X10CrAl18	Z10CAS18	F.3113	1875	0,21	12/13	
95Х18	443S65	HNv6	1.4747	X80CrNiSi20	Z80CSN20.02	F.320B	1875	0,21	12/13		
		446	1.4762	X10CrAl24	Z10CAS24		1875	0,21	12/13		
55Х20Г9АН4	349S54	EV8	1.4871	X53CrMnNiN219	Z52CMN21.09		1875	0,21	12/13		
M	Нержавеющая ферритно/мартенситная и аустенитная сталь										
	X18H10T	321S12	321	1.4541	X10CrNiTi189	Z6CNT18.10	F.3553	2150	0,2	14.1	
	02X18H25M4C3	904S13, 904S14, 904S92	N08904	1.4539	X1 NiCrMoCu25 20 5	Z2 CNDU 25.20		2150	0,2	14.1	
						URANUS B6					
	02X25H22AM2		310MoLN, N08310, S31050	1.4465	X1CrNiMoN 25 22 2	Z2 CND25.22 Az		2150	0,2	14.1	
						CLI UREA 25.22.2					
	03X17H14M3	316S13	316L	1.4404	X2CrNiMo1812,	Z2CND17.12		2150	0,2	14.1	
				1.4435	X2CrNiMo18 14 3						
	03X18H11	304S11	304L	1.4306	X2CrNi1911	Z2CN18-10		2150	0,2	14.1	
	06XH28МДТ		N08028	1.4563	X1 NiCrMoCuN31 27 4	Z1NCDU31-27-03		2150	0,2	14.1	
	08X18H10	304S15	304	1.4301	X6CrNi189	Z6CN18.09	F.3551	2150	0,2	14.1	
	08X18H12B	347S17	347	1.4550	X10CrNiNb189	Z6CnNb18.10	F.3552	2150	0,2	14.1	
	09X17H7Ю1	316S111	17-7PH	1.4568	X7 CrNiAl 17 7	Z8CNA17-07		2150	0,2	14.1	
	10X17H13M2T	320S17	316Ti, 318	1.4571	X10CrNiMoTi1810	Z6NDT17.12	F.3535	2150	0,2	14.1	
			318	1.4583	X10CrNiMoNb1812	Z6CNDNb1713B					
	10X23H18	310S24	310S	1.4845	X12CrNi25 21	Z12CN25 20	F.331	2150	0,2	14.1	
	12X18H9	303S21	301, 303	1.4305	X12CrNiS188	Z10CNF 18.09	F.3508	2150	0,2	14.1	
				1.4310	X12CrNi177	Z12CN17.07	F.3517				
	15X23H18Л			1.4840	G-X15 CrNi 25 20			2150	0,2	14.1	
	15X25T		S44600	1.4746				2150	0,2	14.1	
	15X28		S44600	1.4749		X18 CrN28		2150	0,2	14.1	
	20X23H13	309S24				Z10CNS25.20		2150	0,2	14.1	
	20X23H18	310, 310S24	S31000, S31400	1.4841	X15CrNiSi2520	Z15CNS25-20		2150	0,2	14.1	
	(20X25H20C2)	314S25	J24202			314, SIRIUS 310, 4841, SIRIUS 314		2150	0,2	14.1	
								2150	0,2	14.1	
	40X24H1CЛ	309C30	J93503, J94003	1.4837	G-X40 CrNiSi 25 12			2150	0,2	14.1	
			J94013					2150	0,2	14.1	
		304S11	316	1.4436	X5CrNiMo17 13 3	Z6CND18-12-03		2150	0,2	14.1	
	317S12	317L	1.4438	X2CrNiMo18 16	Z2CND18.15		2150	0,2	14.1		