


Техническое приложение



ISO	Страна							k _c 1.1	m _c	Группа обработки	
	Россия	Великобритания	США	Германия		Франция	Испания				
	Стандарт										
	ГОСТ Р	BS	AISI/SAE	W.-Nr.	DIN	AFNOR	UNF				
N	АД33 (1330, 1340)	6061, HB20 HE20, HG20 L117	A96061, A96205, A96262	3.3315	AlMg1SiCu 6061	6061, A-GSUC A-SGM0.3		700	0,25	22	
	АК4-1		A92618, AA2018, AA2218, AA2618					700	0,25	22	
	АК6							700	0,25	22	
	АК7		A03570, A444.0					700	0,25	22	
	АК8 (1380)	2014A	358.0, A92014, AA2014, AA2214		2014, AlCu4SiMg AlCuSiMn		2014	700	0,25	22	
	АМг2 (1520)	2L55, 5251	A95052, AA5051, AA5151, AA5251, AA5252, AA5351, AA5352, AA5454, AA5552, AA5652		5052, 5251, AlMg2, AlMg2.5, AlMg2Mn0.3	5051, 5052, 505203, A-G2.5C, A-G2M	5052, Al-2Mg	700	0,25	21	
	АМг4 (1540, 1541)		A95086, AA5082, AA5083, AA5086		5086, AlMg4.5Mn AlMg4, AlMg4Mn	5086, A-G4MC	5086, Al-4Mg	700	0,25	21	
	АМг5 (1550, 1556)	5056, 5056A A56S, NB6	A95056, AA5019, AA5056, AA5356, AA5456, AA5556		5019, AlMg5			700	0,25	21	
	АМг6 (1560)	NG61	A95456, A95556			AlMg5Mn	Al-6Mg	700	0,25	21	
	В93							700	0,25	22	
	В95 (1950)	C77S, M75S	AA7075, AA7175, AA7475			A-Z5GU		700	0,25	22	
	В96ц пч		AA7049					700	0,25	22	
	ВД19							700	0,25	22	
	Д1 (1110)		A91110, A92017, AA1110, AA2014, AA2017		AlCu4MgSi AlCuMg1, AlCuSiMn	1110, 131050 A-U4SG	Al-4CuSiMg	700	0,25	22	
	Д16 (1160)	2024	A92024, A92124, AA2024, AA2124	3.1325	2024, AlCuMg2	A-U 4G1	2024	700	0,25	22	
	Д19							700	0,25	23	
	Алюминиевые литые сплавы										
	АК5М4	LM21		3.2551	G-AlSi6Cu4			700	0,25	24	
	АЛ2	AlSi12	A04132, A94047, AlSi12Fe LM20, LM6	3.2581	GK-AlSi12, AlSi12, G-AlSi12	A-S12, A-S13, AlSi12	Al-12SiFe	700	0,25	25	
	АЛ4		360.0, A03600, A360.0	3.2381	G-AlSi10Mg	A-S9GU		700	0,25	24	
	АЛ5	LM16	305.0		G-AlSi5Mg GK-AlSi5MgWa		Al-5SiCuMg	700	0,25	24	
	АЛ5-1		A305.0								
	АЛ9		356, A03560								
	АЛ9-1	LM25	356, A03560	3.2371	G-AlSi7Mg		AlSi7Mg	700	0,25	24	
	АЛ19				AlCu4Ti						
	АЛ22							700	0,25	23	
	АЛ24		A07070				707	700	0,25	23	
	АЛ27	LM10	520, A05200					700	0,25	24	
	АЛ30	LN13	A03360		AlSi12CuNiMg	A-Si12UGN		700	0,25	23	
	АЛ32		A03280					700	0,25	24	
	АЛ34		358.0					700	0,25	24	
	АМг4К1,5М			3.3261	G-AlMg5Si			700	0,25	24	
	ВАЛ8		A380.0, A380.1	3.2163	G-AlSi9Cu3			700	0,25	24	
	Медные сплавы										
	ЛС60-2	CZ124	C35330, C36000	2.0375	CuZn36Pb3	CuZn36Pb3		700	0,27	26	
	ЛС63-3	CZ119	C35300, C35600					700	0,27	26	
	ЛО62-1	CZ112	C46200, C46400		CuZn38Sn1			700	0,27	27	
	ЛМц58-2		C67410		CuZn40Mn2			700	0,27	27	
	Л63	CZ108	C27200	2.0321	CuZn37	CuZn36, CuZn37		700	0,27	27	
	Л70	CZ106	C26000	2.0265	CuZn30	CuZn30		700	0,27	27	
	Л85	CZ102	C23000	2.0240	CuZn15	CuZn15		700	0,27	27	